Technical Data Sheet

Product name: ApolloX™

Date of issue: 22 April 2016
Version: v1

ApolloX™ is a professional high strength & performance engineering filament based on a uniquely industrial-grade modified ASA (Acrylonitrile Styrene Acrylate) compound. ApolloX™ has been modified to have great thermal stability & improved filament flow behavior and has zero-warping and flawless first- and interlayer adhesion allowing you to 3D print objects with an almost injection molding precision.
ApolloX™ is UV & weather resistant ensuring great color stability – combined with high strength and heat resistant properties – which makes ApolloX™ a perfect engineering filament for outdoor and automotive applications.

Properties	Typical value	Test Method	Test condition
Physical			
Specific gravity	1.11 g/cc	ISO 1183	-
Melt flow rate	45 g/10min	ISO 1133	260° C/5Kg
Water absorption	-	-	-
Moisture absorption	-	-	-
Mechanical			
Impact strength	18 KJ/m²	ISO 179	Charpy Notched @23° C (73° F)
Tensile strength	47,5 Mpa	ISO 527	@Yield 50mm/min (2 inch/min)
Tensile modulus	2020 Mpa	ISO 527	1mm/min
Elongation at break	15%	ISO 527	@ Break 50mm/min (2 inch/min)
Flexural strength	-	-	-
Flexural modulus	-	-	-
Hardness	-	-	-
Thermal			
Print temperature	± 235 - 255° C	-	-
Melting termperature	± 230 ± 10° C	ISO 294	-
Viscat softening temp.	± 98° C	ISO 306	VST/A/50 (50° C/h, 10N)
Optical			
Haze	-	-	-
Transmittance	-	-	-
Gloss	-	-	-

Product details, certifications and compliance	
HS Code	39169090
REACH compliant	Yes
RoHS certified	Yes
FDA compliant	Yes

Diameter	Tolerance	Roundness
1.75mm	± 0.05mm	≥ 95%
2.85mm	± 0.10mm	≥ 95%

Formfutura VOF
Groenestraat 215
6531 HH Nijmegen
The Netherlands

CoC: 55502105
VAT: NL851741083B01
EORI: NL851741083

Tel: +31 (0)85 002 0881
Email: info@formfutura.com
Website: www.formfutura.com

All information supplied by or on behalf of Formfutura in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but Formfutura assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the forementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications.